

Orthorhombic domains in powder RuO₂ at ambient conditions

W. Lulka^{1*}, R. Przeniosła¹, I. Sosnowska¹, F. Fauth² and E. Suard³


¹Faculty of Physics, University of Warsaw, 02-093 Warsaw, Poland

²ALBA-CELLS BP1413 08290, Cerdanyola del Valles, Barcelona, Spain

³Institut Laue Langevin, 38042 Grenoble, France

*e-mail: Wojciech.Lulka@fuw.edu.pl

The crystal structure of the tentative altermagnet RuO₂ was studied by synchrotron radiation based x-ray powder diffraction, constant-wavelength neutron powder diffraction and time-of-flight neutron powder diffraction. The diffraction patterns are best described by Rietveld refinement with the anisotropic Bragg peaks' broadening model. The distribution of the RuO₂ crystallites is composed of a majority of orthorhombic domains (space group *Pnmm*) which coexist with a minority of tetragonal domains (space group *P4₂/mmm*).



In order to demonstrate the changes of fit quality we have done Rietveld refinements with the orthorhombic symmetry (space group *Pnmm*) for fixed values of the *a* and *b* lattice parameters calculated as:

$$a = \langle a \rangle \left(1 + \frac{r}{2} \right); \quad b = \langle a \rangle \left(1 - \frac{r}{2} \right)$$

where $\langle a \rangle$ is the average of *a* and *b* obtained in the orthorhombic fit while the orthorhombic deformation parameter *r* changes between $-0.0057 < r < 0.0057$ with a fixed step. All instrumental, background and structural parameters (except fixed *a* and *b*) were refined. Please note that $r = 0$ corresponds to the tetragonal rutile-type fit. The value of $\chi^2(r)$ for the best fit at each value of *r* is drawn with solid symbols. The curves drawn show the fourth-order even polynomial $f(r) = ar^4 + br^2 + c$ fitted with very good agreement to the observed $\chi^2(r)$ for all three datasets. The results of SXRPD and NPD show good correspondence with each other with a double

minimum of $\chi^2(r)$ near $r = 0.0036$. The neutron diffraction n-TOF pattern measured with a powder RuO₂ sample from a different batch than the first two gives also a clear minimum near $r = 0.0032$.

Acknowledgements: Thanks are due to Julien Haines for providing the neutron TOF data for powder RuO₂ published in [1]. CELLS-ALBA is acknowledged for in-house beam time allocation of Project ID 2020104796. The Ministry of Education and Science (Poland) is acknowledged for funding.

References

1. J. Haines, J. M. Leger, O. Schulte, and S. Hull, Neutron Diffraction Study of the Ambient-Pressure, Rutile-Type and the High-Pressure, CaCl₂-Type Phases of Ruthenium Dioxide, Acta Crystallographica Section B 53 (1997) 880.